

loaded structures, degradation models, improved slow and fast computation tools for statically loaded structures as well as design guidelines, which take skin stringer separation and material degradation into account. The experimental data base is indispensable for validation of the analytically developed degradation models, which will be implemented into the new tools, and for verification of the computed results as well. Reliable fast tools will allow for an economic design process, whereas very accurate but necessarily slow tools are required for the final certification.

Although, with respect to loads and characteristic dimensions, this project is oriented towards an application in the fields of fuselage structures, the results will be transferable to other airframe structures as well. With the new design guidelines the European aircraft industry

will have a tool at its disposal, which substantially contributes to the objectives of reducing development and operating costs, by 20 % and 50 % in the short and long term, respectively. That provides the chance for decisive improvements in competitiveness of future European aircraft.

The traditional aircraft design can be replaced by an advanced procedure including degradation models for composite structures. One main benefit of the application of the new tools and design guidelines will be a considerably reduced structural weight at safety not impaired. In addition, the developed tools also reduce the design and analysis time by one order of magnitude and thus, they substantially improve response-to-market time of industrial developments.

Table 1 · Participants

Organisation name	Contact person	Country	FAX
German Aerospace Center (DLR)	Dr. R. Degenhardt	DE	+49 531 295 2232
AGUSTA	Mr. G. Pagnano	IT	+39 0331 711813
Gamesa Aeronáutica	Mr. F. R. Arribas	ES	+34 945 185 685
Hellenic Aerospace Industry (HAI)	Dr. Z. Marioli-Riga	GR	+30 2 262 0 52170
Israel Aircraft Industries Ltd. (IAI)	Mrs. G. Ghilai	IL	+972 3 9355055
PZL-Swidnik S.A.	Mr. P. Chojnacki	PL	+48 81 4680976
Samtech S.A.	Ms. C. Bon	BE	+32 4 361 69 80
SMR S.A.	Dr. S. Merazzi	CH	+41 32 345 2120
Cooperative Research Centre for Advanced Composite Structures (CRC-ACS)	Prof. M. Scott	AU	+61 3 9646 8352
The Swedish Defence Research Agency (FOI)	Dr. R. Jarlas	SE	+46 8 5550 3062
Karlsruhe University (UKA)	Prof. W. Wagner	DE	+49 721 608 6015
Politecnico di Milano (POLIMI)	Prof. C. Bisagni	IT	+39 02 23998334
Riga Technical University (RTU)	Prof. R. Rikards	LV	+371 708 9254
RWTH Aachen	Prof. H.-G. Reimerdes	DE	+49 241 8092230
Israel Institute of Technology (TECHNION)	Prof. H. Abramovich	IL	+972 4 8292030

For further information on this project, please contact the co-ordinator:

Dr. Richard Degenhardt

DLR, Institute of Composite Structures and Adaptive Systems
Lilienthalplatz 7
38108 Braunschweig
Germany

Tel. +49 531 295 3059 · Fax +49 531 295 2232
E-mail: richard.degenhardt@dlr.de

For information on the Sixth Framework Programme, please contact the Scientific Officer for the project:

Dr. Hans Josef von den Driesch

European Commission,
DG RTD
CDMA 21 4/172
1049 Bruxelles
Belgium

Tel. +32 229 60 609 · Fax: +32 229 66 757
E-mail: hans-josef.von-den-driesch@cec.eu.int



Specific Targeted Research Project
funded by the European Community
Thematic Priority 4 – Aeronautics and Space



COCOMAT

Improved **MAT**erial Exploitation
at Safe Design of **CO**mposite Airframe Structures by
Accurate Simulation of **CO**llapse

www.cocomat.de

INTRODUCTION

The project COCOMAT (Improved Material Exploitation at Safe Design of Composite Airframe Structures by Accurate Simulation of Collapse) is a Specific Targeted Research Project within the 6th Framework Programme (No. AST3-CT-2003-502723) and will run for 4 years (2004-2007).

European aircraft industry demands for reduced development and operating costs, by 20 % and 50 % in the short and long term, respectively. The COCOMAT project contributes to this aim by reducing structural weight at safe design; it exploits considerable reserves in primary fibre composite fuselage structures by accurate and reliable simulation of collapse. Collapse is specified by that point of the load-shortening curve where a sharp decrease occurs thus limiting the load carrying capacity.

COCOMAT is fully based upon the results of the finished Fifth Framework project POSICOSS (Improved Postbuckling Simulation for Design of Fibre Composite Stiffened Fuselage Structures) which developed improved, fast and reliable procedures for buckling and postbuckling analysis of fibre composite stiffened panels of future fuselage structures, created experimental data bases (cf. Figure 1) and derived design guidelines (www.posicoss.de).

The COCOMAT project extends the POSICOSS results and goes beyond by accounting for degradation. That requires knowing about degradation due to static as well as low cycle loading in the postbuckling range. It is well-known that thin-walled structures made of carbon fibre reinforced plastics are able to tolerate repeated buckling without any change in their buckling behaviour. However, it has to be found out, how deep into the postbuckling regime one can go without severely damaging the structure, and how this can be predicted by fast and precise simulation procedures. This issue is dealt with by COCOMAT.

PROJECT OBJECTIVES

COCOMAT mainly strives for accomplishing the large step from the current to a future design scenario of stringer stiffened composite panels demonstrated in Figure 2. The left graph illustrates a simplified load-shortening curve and highlights the current industrial design scenario. Three different regions can be specified. Region I covers loads allowed under operating flight

conditions and is bounded above by limit load; region II is the safety region and extends up to ultimate load; region III comprises the not allowed area which reaches up to collapse. There is still a large unemployed structural reserve capacity between the current ultimate load and collapse. The right graph of Figure 2 depicts the design scenario aspired in future, where ultimate load is shifted towards collapse as close as possible. Another main difference to the current design scenario is that the onset of degradation is moved from the not allowed region III to the safety region II due to reliable simulation of collapse. This is comparable to metallic structures where plasticity is already permitted in the safety region. However, it must be guaranteed that in any case the onset of degradation must not occur below limit load. Moreover, the extension requires an accurate and reliable simulation of collapse, which means to take into account degradation under static as well as under low cycle loading, in addition to geometrical nonlinearity.

PARTICIPANTS

The COCOMAT consortium (cf. Table 1) merges knowledge from 5 large industrial partners (AGUSTA from Italy, GAMESA from Spain, HAI from Greece, IAI from Israel and PZL from Poland), 2 partners belonging to the category of Small and Medium Enterprises (SAMTECH from Belgium and SMR from Switzerland), 3 research establishments (DLR from Germany, FOI from Sweden and CRC-ACS from Australia) and 5 universities (Politecnico di Milano from Italy, RWTH Aachen and University of Karlsruhe from Germany, TECHNION from Israel and Technical University of Riga from Latvia).




Figure 1 · Out-of-plane deformations of one tested POSICOSS panel




Figure 2 · Current and future design scenarios for typical stringer stiffened composite panel

DESCRIPTION OF WORK

The partners co-operate in the following six technical work packages:

- Benchmarking on collapse analysis of undamaged and damaged panels with existing tools: Knowledge of the partners is compared and the deficiencies of existing software are identified.
- Material characterisation, degradation investigation and design of panels for static and cyclic tests: Material properties are characterized, degradation models are developed and test panels are designed as to the requirements of research in order to overcome the deficiencies.
- Development of improved simulation procedures for collapse: Slow certification and fast design tools are developed and validated by the tests.
- Manufacture, inspection and testing by static and cyclic loading of undamaged panels: The experimen-

tal data base is extended by testing of undamaged panels.

- Manufacture, inspection and testing by static and cyclic loading of pre-damaged panels: The experimental data base is extended by testing of pre-damaged panels.
- Design guidelines and industrial validation: All project results are assembled and final design guidelines are derived. The tools are validated by the industrial partners.

Industrial partners bring in their experience with design and manufacture of real shells; research partners contribute knowledge on testing and on development of simulation tools. Design guidelines are defined in common, and the developed tools are validated by the industrial partners.

EXPECTED RESULTS AND BENEFITS

The project results will comprise a substantially extended data base on material properties and on collapse of undamaged and pre-damaged statically and cyclically

